

CERTIFICATE OF TRANSMISSION BY FACSIMILE (37 CFR 1.8)		Docket No. 98-2069	
Applicant(s): Guidotti, et al.			
Serial No. 09/432,334	Filing Date November 2, 1999	Examiner J. Maples	Group Art Unit 1745


Invention: **ENERGY STORAGE AND CONVERSION DEVICES USING THERMAL SPRAYED ELECTRODES**

I hereby certify that this Letter (2 pages) and Corrected Declaration (3 pages)
(Identify type of correspondence)

is being facsimile transmitted to the United States Patent and Trademark Office (Fax. No. (703) 872-9311)

on July 15, 2002
(Date)

Tracy A. Sweatt
(Typed or Printed Name of Person Signing Certificate)



(Signature)

Note: Each paper must have its own certificate of mailing.

FAX RECEIVED
JUL 15 2002
GROUP 1700

OFFICIAL

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICANT: GUIDOTTI ET AL.

SERIAL NUMBER: 09/432,334

FILED: 11/2/99

FOR: ENERGY STORAGE AND
CONVERSION DEVICES USING
THERMAL SPRAYED
ELECTRODES

Group Art Unit: 1745

Examiner: J. Maples

DECLARATION PURSUANT TO 37 C.F.R. § 1.132

The Assistant Commissioner of Patents
Washington, D.C. 20231

Sir:

Tongsan D. Xiao, declares and says that:

1. I have worked in the field of thermally sprayed coatings for 10 years. I am an inventor of the above referenced patent application.

2. I have read, understood, and am familiar with the above-referenced application. I have also read, understood, and am familiar with the U.S. Patent No. 5,716,422 to Muffoletto et al.

3. During initial investigations into thermally spraying active materials that are thermally unstable at thermal spray temperatures, attempts were made to form an FeS₂ (pyrite) coating by thermally spraying FeS₂ as described by Muffoletto. First attempts employed high-velocity oxygen flame (HVOF). These attempts were unsuccessful in that

#22
7.18.2FAX RECEIVED
JUL 15 2002
OFFICIAL
GROUP 1700

FeS₂ was not deposited. The deposited material was analyzed by X-ray diffraction (XRD) and was found to be primarily Fe₂O₃. Further attempts to obtain an FeS₂ coating employed dc-arc plasma spray under an argon cover (250 SCFH) with arc currents of between 200 and 300 A. XRD of the deposited material indicated Fe₇S₈ and not FeS₂. Representative data is shown in Fig. 1 attached hereto.

4. FeS₂ was plasma sprayed with elemental sulfur. The primary phase of the resulting deposit (>95%) was FeS₂ as shown by the X-ray data in Figure 1.

5. Discharge traces were recorded for cells employing natural FeS₂, FeS₂ plasma sprayed without sulfur and FeS₂ plasma sprayed with sulfur. These discharge traces are shown in Fig. 2 attached hereto. The discharge traces corroborate the above described XRD data in that the FeS₂ plasma sprayed without sulfur exhibits a significantly different trace than the natural pyrite and the FeS₂ plasma sprayed with sulfur. Additionally the discharge traces of the cell employing FeS₂ plasma sprayed with sulfur paralleled the discharge traces of the cell employing natural pyrite.

6. Thus, based on my knowledge of the thermal spray field and the above described experiments and data, I believe the presence of a protective coating such as elemental sulfur is to be necessary to produce a thermally sprayed electrode comprising FeS_2 or other material that is unstable at thermal spray temperatures.

7. I declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or document or any patent resulting therefrom.

Date: _____

7/1/02



Tongsan D. Xiao